


AD-A195 952 THE EFFECT OF NOTCH ROOT RADIUS ON THE DETERMINATION OF 1/1
TOUGHNESS IN ULTR. (U) ARMY LAB COMMAND WATERTOWN MA
MATERIAL TECHNOLOGY LAB W S RICCI ET AL. JUN 88
UNCLASSIFIED MTL-TR-88-21 F/G 11/6.1 NL





UTION TEST CHART
 1000 1.52 A

2

MTL TR 88-21

AD

AD-A195 952

THE EFFECT OF NOTCH ROOT RADIUS ON THE DETERMINATION OF TOUGHNESS IN ULTRAHIGH STRENGTH STEEL FRICTION WELDS

WILLIAM S. RICCI

FABRICATION & TECHNOLOGY DEMONSTRATION BRANCH

ERIC B. KULA

METALS RESEARCH BRANCH

June 1988

Approved for public release; distribution unlimited.



US ARMY
LABORATORY COMMAND
MATERIALS TECHNOLOGY LABORATORY

DTIC
ELECTE
AUG 01 1988
S D
CH

U.S. ARMY MATERIALS TECHNOLOGY LABORATORY
Watertown, Massachusetts 02172-0001

88 Y 20 12

The findings in this report are not to be construed as an official Department of the Army position, unless so designated by other authorized documents.

Mention of any trade names or manufacturers in this report shall not be construed as advertising nor as an official indorsement or approval of such products or companies by the United States Government.

DISPOSITION INSTRUCTIONS

Destroy this report when it is no longer needed.
Do not return it to the originator.

UNCLASSIFIED

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

REPORT DOCUMENTATION PAGE		READ INSTRUCTIONS BEFORE COMPLETING FORM
1. REPORT NUMBER MTL TR 88-21	2. GOVT ACCESSION NO. ADA195-952	3. RECIPIENT'S CATALOG NUMBER
4. TITLE (and Subtitle) THE EFFECT OF NOTCH ROOT RADIUS ON THE DETERMINATION OF TOUGHNESS IN ULTRAHIGH STRENGTH STEEL FRICTION WELDS		5. TYPE OF REPORT & PERIOD COVERED Final Report
		6. PERFORMING ORG. REPORT NUMBER
7. AUTHOR(s) William S. Ricci and Eric B. Kula		8. CONTRACT OR GRANT NUMBER(s)
9. PERFORMING ORGANIZATION NAME AND ADDRESS U.S. Army Materials Technology Laboratory Watertown, Massachusetts 02172-0001 SLCMT-MEF		10. PROGRAM ELEMENT, PROJECT, TASK AREA & WORK UNIT NUMBERS D/A Project: 1L263102D071
11. CONTROLLING OFFICE NAME AND ADDRESS U.S. Army Laboratory Command 2800 Powder Mill Road Adelphi, Maryland 20783-1145		12. REPORT DATE June 1988
		13. NUMBER OF PAGES 5
14. MONITORING AGENCY NAME & ADDRESS (if different from Controlling Office)		15. SECURITY CLASS. (of this report) Unclassified
		15a. DECLASSIFICATION/DOWNGRADING SCHEDULE
16. DISTRIBUTION STATEMENT (of this Report) Approved for public release; distribution unlimited.		
17. DISTRIBUTION STATEMENT (of the abstract entered in Block 20, if different from Report)		
18. SUPPLEMENTARY NOTES		
19. KEY WORDS (Continue on reverse side if necessary and identify by block number) Welding Toughness Inertia Impact Friction Steel Fracture (mechanics)		
20. ABSTRACT (Continue on reverse side if necessary and identify by block number) (SEE REVERSE SIDE)		

UNCLASSIFIED

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

Block No. 20

ABSTRACT

The plain strain fracture toughness and Charpy impact energy of friction welds in ultrahigh strength AISI 4340 steel were determined. Fracture toughness values for the weld zone were found to exceed those of the base metal. This is believed to be due to the larger prior austenite grain size in the weld zone resultant from the weld thermal cycle. Charpy impact energy data for the weld zone, however, were approximately 50 percent lower than those of the base metal. This was due to the adverse reorientation of sulfide inclusions in the weld zone resulting from the forging stage of the welding cycle. Discrepancies between fracture toughness and Charpy impact test data can be attributed to notch root radius effects. The use of both sharp notch and rounded notch toughness tests are recommended for the determination of weld joint ductility in ultrahigh strength steels. *Keywords: Inertia Welding; Friction Welding; Notch Toughness. (AW).*



Accession For	
NTIS GRA&I	<input checked="" type="checkbox"/>
DTIC TAB	<input type="checkbox"/>
Unannounced	<input type="checkbox"/>
Justification	
By	
Distribution/	
Availability Codes	
Dist	Avail and/or Special
A-1	

UNCLASSIFIED

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

INTRODUCTION

Inertia welding, a form of friction welding, is a solid state joining process that produces bonding using the heat developed between two surfaces during mechanically induced rubbing motion. The inertia welding cycle can be divided into two stages: the friction stage, and the upsetting or forging stage. Welding heat is developed during the first stage, and the weld is consolidated and cooled during the second stage. A complete description of the inertia welding process is presented elsewhere.¹

It is well known that for any steel worked principally in one direction, the mechanical properties, especially ductility, in the direction of working are different from those in the perpendicular or short transverse direction.^{2,3} On application of forging pressure during an inertia weld, metal is forced out in a radial direction normal to the forging direction. Consequently, any inclusions in the weld zone initially oriented parallel to this major working direction are reoriented into a direction normal to this axis within the bond zone during the forging stage. Short transverse base metal properties should, therefore, be expected across inertia welded joints.⁴

The effects of sulfur concentration and precrack location on the plain strain fracture toughness properties of inertia welds in 4340 steel at moderate strength and low sulfur levels have previously been evaluated.⁴ Speich⁵ demonstrated that variations in sulfide inclusion shape and concentration have a negligible effect on Charpy impact energy at high strength levels for 4340 steel. Ritchie showed that the contradictory results of the plain strain fracture toughness (K_{IC}) and Charpy impact energy tests can be rationalized in terms of the response of notch root radius on toughness. The purpose of the work reported here was to evaluate the use of percent elongation, plain strain fracture toughness, and Charpy impact energy as measures of ductility for inertia welded joints in AISI 4340 steel at ultrahigh strength levels, approximately 300 ksi.

EXPERIMENTAL

Seamless tubing (6.25" outer diameter with a wall thickness of 0.5") from an electric furnace melted heat of AISI 4340 steel was inertia welded. The chemical composition of the material tested is shown in Table 1. Carbon and sulfur were measured by combustion techniques; all other elements were analyzed by emission spectroscopy.

Table 1. CHEMICAL COMPOSITION OF THE MATERIAL TESTED

	Weight Percent									
	C	S	Mn	P	Si	Ni	Cr	Mo	Cu	Al
Heat #1	0.45	0.006	0.70	0.015	0.26	1.82	0.81	0.27	0.11	0.04
Typical 4340	0.38-0.43	0.04	0.60-0.80	<0.035	0.20-0.30	1.65-2.00	0.70-0.90	0.20-0.30	-	-

1. Welding Handbook, vol. 3, *Resistance and Solid-State Welding and Other Joining Processes*. 7th Edition, W. H. Kearns, ed, American Welding Society, Miami, Florida, 1980, p. 244.
2. PORTER, L. F. *Lamellar Tearing in Plate Steels (a Literature Survey)*. AISI, August 1975.
3. SKINNER, D. H., and TOYAMA, M. *Through Thickness Properties and Lamellar Tearing*. Welding Res. Bull., 1977, v. 232, p. 1-20.
4. RICCI, W. S., KULA, E. B., COLGATE, J. D. *Effects of Sulfur Content on the Plain Strain Fracture Toughness of Inertia Welds in 4340 Steel*. U.S. Army Materials Technology Laboratory, MTL TR 87-53, September 1987.
5. SPEICH, G. R., and SPITZEG, W. A. *Effect of Volume Fraction and Shape of Sulfide Inclusions on Through Thickness Ductility and Impact Energy of High Strength 4340 Plate Steel*. Metall. Trans. A, v. 13A, December 1982, p. 2239-2258.

All welds were fabricated in accordance with MIL-STD-1252 for Type I, Class B welds. A fly wheel speed of 1225 rpm and forging pressure of 3400 psi were used. Work pieces were heat treated, prior to and after welding, according to the process schedule shown in Figure 1.




Figure 1. Heat treatment schedule.

Type TR-3A, 0.252" diameter, threaded, round, tensile specimens and Type CV-2, 0.394" x 0.394" x 2.165" Charpy V-notched specimens were machined from each quadrant of the welded section. Flood coolant conditions were used to prevent burning. The weld line was located in the center of each specimen. Notches were machined in the Charpy specimens to provide an L-C crack plane orientation. The specimens used to evaluate fracture toughness were Charpy specimens precracked by bending fatigue loading. Fracture toughness data were obtained in slow bending, in accordance with ASTM E 399. Charpy specimens were broken in a pendulum type impact machine with the hammer velocity of approximately 17 feet per second, in accordance with ASTM E 23.

RESULTS AND DISCUSSION

Mechanical property data including tensile, Charpy impact, and fracture toughness data for the base metal and weld are shown in Table 2.

Weld zone fracture toughness data exceeded that of the base metal. This is believed to have been due to the larger prior austenite grain size in the weld zone resultant from the weld thermal cycle.⁶ Other indicators of weld joint toughness

6. RITCHIE, R. O., FRANCIS, B., and SERVER, W. L. *Evaluation of Toughness in AISI 4340 Alloy Steel Austenitized at Low and High Temperatures*. Metall. Trans. A, v. 7A, June 1976, p. 831-838.

Table 2. MECHANICAL PROPERTIES OF BASE METAL AND WELD JOINTS

	YS 0.2% Offset (ksi)	URS (ksi)	Elong. (%)	Charpy Impact Energy, 77°F (ft-lb)	Charpy Impact Energy, -25°F (ft-lb)	K _{IC} , 77°F (ksi √in.)	K _{IC} , -25°F (ksi √in.)
Base Metal	226.9 (0.73)*	298.1 (0.87)	11.9 (0.1)	11.9 (0.35)	9.7 (0.64)	37.8 (0.64)	36.28 (1.23)
Weld	218.7 (2.31)	294.0 (5.29)	4.85 (0.64)	6.37 (0.45)	5.5 (1.63)	45.93 (1.25)	39.42 (1.70)

*Standard Deviation

and ductility, i.e., Charpy impact energy and percent elongation, showed weld zone values approximately 50 percent lower than the unaffected base metal values. Weld zone results for these tests approximated those expected for the short transverse orientation in the base metal.

The major differences between the fracture toughness and Charpy tests can be summarized as follows: 1) the Charpy specimen contains a V-notch ($\rho = 0.25$ mm), whereas the fracture toughness specimen contains a fatigue precrack ($\rho \rightarrow 0$), 2) the strain rate for the Charpy test is greater than that of the fracture toughness test, and 3) the Charpy test measures the energy required to initiate and propagate a crack and, therefore, includes a contribution from plain stress, whereas the fracture toughness test measures the stress intensity at a crack tip necessary to cause plain strain crack growth only. Ritchie⁶ determined that the observed discrepancy between the fracture toughness and the Charpy impact tests was primarily due to notch root radius effects. The evaluation of friction weld joint toughness should not, therefore, be based on either tensile fracture toughness or Charpy impact data alone but should include both infinitely sharp notch and rounded notch toughness tests.

SUMMARY

Fracture toughness tests of friction welded joints in ultrahigh strength steels showed weld joint values exceeding those of the base metal. The reason for this is believed to be due to the larger prior austenite grain size in the weld zone resultant from the weld thermal cycle.

Charpy impact energy data for the weld zone in friction welded joints were found to be approximately 50 percent lower than those of the unaffected base metal. The reason for this is the adverse reorientation of nonmetallic inclusions in the weld zone resultant from the forging stage of the welding cycle.

Discrepancies between the Charpy impact and the fracture toughness test data are believed to be primarily due to notch root radius effects. Both sharp crack fracture toughness and rounded notch impact energy tests are, therefore, required for the complete evaluation of friction weld joint toughness and ductility.

DISTRIBUTION LIST

No. of Copies	To
1	Office of the Under Secretary of Defense for Research and Engineering, The Pentagon, Washington, DC 20301
	Commander, U.S. Army Laboratory Command, 2800 Powder Mill Road, Adelphi, MD 20783-1145
1	ATTN: AMSLC-IM-TL
	Commander, Defense Technical Information Center, Cameron Station, Building 5, 5010 Duke Street, Alexandria, VA 22304-6145
2	ATTN: DTIC-FDAC
	Metals and Ceramics Information Center, Battelle Columbus Laboratories, 505 King Avenue, Columbus, OH 43201
1	ATTN: Mr. Robert J. Fiorentino, Program Manager
1	Defense Advanced Research Projects Agency, Defense Sciences Office/MSD, 1400 Wilson Boulevard, Arlington, VA 22209
	Headquarters, Department of the Army, Washington, DC 20314
1	ATTN: DAEN-RDM, Mr. J. J. Healy
	Commander, U.S. Air Force Wright Aeronautical Laboratories, Wright-Patterson Air Force Base, OH 45433
1	ATTN: AFWAL/MLC
1	AFWAL/MLLP, D. M. Forney, Jr.
1	AFWAL/MLBC, Mr. Stanley Schulman
1	AFWAL/MLLS, Dr. Terence M. F. Ronald
1	AFWAL/FIBEC, Dr. Steve Johnson
1	Edward J. Morrissey, AFWAL/MLTE, Wright-Patterson Air Force Base, OH 45433
	Commander, Army Research Office, P.O. Box 12211, Research Triangle Park, NC 27709-2211
1	ATTN: Information Processing Office
1	Dr. George Mayer
	Commander, U.S. Army Materiel Command, 5001 Eisenhower Avenue, Alexandria, VA 22333
1	ATTN: AMCLD
	Commander, U.S. Army Armament, Munitions and Chemical Command, Dover, NJ 07801
1	ATTN: Mr. Harry E. Pebly, Jr., PLASTEC, Director
	Commander, U.S. Army Aviation Systems Command, 4300 Goodfellow Blvd., St. Louis, MO 63120
1	ATTN: AMDAV-NS, Harold Law
	Director, U.S. Army Ballistic Research Laboratory, Aberdeen Proving Ground, MD 21005
1	ATTN: SLCBR-TSB-S (STINFO)
	Commander, U.S. Army Electronics Research and Development Command, Fort Monmouth, NJ 07703
1	ATTN: AMDSD-L
1	AMDSD-E
	Commander, U.S. Army Foreign Science and Technology Center, 220 7th Street, N.E., Charlottesville, VA 22901
1	ATTN: Military Tech
	Commander, U.S. Army Materiel Systems Analysis Activity, Aberdeen Proving Ground, MD 21005
1	ATTN: AMXSU-MP, H. Cohen
	Commander, U.S. Army Missile Command, Redstone Scientific Information Center, Redstone Arsenal, AL 35898-5241
1	ATTN: AMSMI-RD-CS-R/ILL Open Lit
1	AMSMI-RLM
1	AMSMI-RLA, Dr. James J. Richardson

No. of Copies	To
	Commander, U.S. Army Belvoir Research, Development and Engineering Center, Fort Belvoir, VA 22060-5606
1	ATTN: STRBE-D
1	STRBE-FS, Fuel & Water Supply Division
1	STRBE-N
1	STRBE-VL
	Commander, U.S. Army Aviation Applied Technology Directorate, Aviation Research and Technology Activity (AVSCOM), Fort Eustis, VA 23604-5577
1	ATTN: SAVRT-TY-ATP, Mr. James Gomez, Aerospace Engineer
	Commander, U.S. Army Tank-Automotive Command, Warren, MI 48090
1	ATTN: AMSTA-RCKM
	Director, Benet Weapons Laboratory, LCWSL, USA AMCOM, Watervliet, NY 12189
1	ATTN: AMSMC-LCB-TL
1	AMSMC-LCB-PS, Dr. I. Ahmad
	David Taylor Naval Ship Research and Development Center, Annapolis, MD 21402
1	ATTN: Dr. Michael Vassilaros - Code 2814
	Office of Naval Technology, 800 N. Quincy Street, Arlington, VA 20017
1	ATTN: Mr. J. J. Kelly - Code MAT 0715
	Naval Research Laboratory, Washington, DC 20375
1	ATTN: Code 5830
1	Dr. G. R. Yoder - Code 6384
1	Dr. S. C. Sanday - Code 6370
	Chief of Naval Research, Arlington, VA 22217
1	ATTN: Code 471
1	Dr. Steven G. Fishman
	Naval Sea Systems Command, Washington, DC 20362
1	ATTN: Mr. Marlin Kinna - 62R4
	Naval Air Development Center, Warminster, PA 18974
1	ATTN: Dr. E. U. Lee - Code 60632
	Naval Surface Weapons Center, White Oak, Silver Spring, MD 20910
1	ATTN: John V. Foltz - Code R32
1	Dr. Herbert Newborn - Code R34
	National Aeronautics and Space Administration, Washington, DC 20546
1	ATTN: Mr. Michael A. Greenfield, Program Manager for Materials, Code RTM-6
	National Aeronautics and Space Administration, Lewis Research Center, Cleveland, OH 44135
1	ATTN: Dr. James A. DiCarlo, Mail Stop 106-1
	National Aeronautics and Space Administration, Marshall Space Flight Center, Huntsville, AL 35812
1	ATTN: R. J. Schwinghammer, EH01, Dir, M&P Lab
1	Mr. W. A. Wilson, EH41, Bldg. 4612
	The Boeing Vertol Company, P.O. Box 16858, Philadelphia, PA 19142
1	ATTN: Mr. Robert L. Pinckney, Mail Stop P62-06
1	Mr. Joseph W. Lenski, Jr., Mail Stop P32-09
	E. I. DuPont De Nemours and Company, Inc., Textile Fibers Department, Pioneering Research Laboratory, Experimental Station, Wilmington, DE 19898
1	ATTN: Blake R. Bichlmeir
	Mr. Rex C. Claridge, TRW, Incorporated, Manufacturing Division, Mail Stop 01-2210, 1 Space Park, Redondo Beach, CA 90278
1	Dr. James A. Cornie, Materials Processing Center, Bldg. 8, Room 237, Massachusetts Institute of Technology, 77 Massachusetts Avenue, Cambridge, MA 01239

No. of Copies	To
1	Dr. Bhagwan K. Das, Engineering Technology Supervisor, The Boeing Company, P.O. Box 3999, Seattle, WA 98124
1	Leroy Davis, NETCO, 592 Dryad Road, Santa Monica, CA 9042-1318
1	Mr. Joseph F. Dolowy, Jr., President, DWA Composite Specialties, Inc., 21133 Superior Street, Chatsworth, CA 91311
1	Mr. Robert E. Fisher, President, AMERCOM, Inc., 8948 Fullbright Avenue, Chatsworth, CA 91311
1	Mr. Louis A. Gonzalez, Kaman Tempo, 816 State Street, Santa Barbara, CA 93101
1	Prof. James G. Goree, Dept. of Mechanical Engineering, Clemson University, Clemson, SC 29631
1	William F. Grant, AVCO Specialty Materials Division, 2 Industrial Avenue, Lowell, MA 01851
1	Mr. Jacob Gubbay, Charles Stark Draper Laboratories, 555 Technology Square, Mail Station 27, Cambridge, MA 02139
1	Mr. John E. Hack, Southwest Research Institute, 6220 Culebra Road, San Antonio, TX 78284
1	Dr. H. A. Katzman, The Aerospace Corporation, P.O. Box 92957 Los Angeles, CA 90009
	Lockheed California Company, Burbank, CA 91520
1	ATTN: Mr. Rod F. Simenz, Department of Materials and Processes
	Lockheed Georgia Company, 86 South Cobb Drive, Marietta, GA 30062
1	ATTN: Materials and Processes Engineering Department
1	Mr. James Carroll
	Material Concepts, Inc., 2747 Harrison Road, Columbus, OH 43204
1	ATTN: Mr. Stan J. Paprocki
1	Mr. David Goddard
1	Dr. Mohan S. Misra, Martin Marietta Aerospace, P.O. Box 179, Denver, CO 80201
1	Mr. Patrick J. Moore, Staff Engineer, Lockheed Missiles and Space Company, Organization 62-60, Building 104, P.O. Box 504, Sunnyvale, CA 94086
1	R. Byron Pipes, Professor & Director, Center for Composite Materials, University of Delaware, Newark, DE 19711
1	Dr. Karl M. Prewo, Principal Scientist, United Technologies Research Center, Mail Stop 24, East Hartford, CT 06108
1	Dr. B. W. Rosen, Materials Sciences Corporation, Gwynedd Plaza 11, Bethlehem Pike, Spring House, PA 19477
1	Prof. Marc H. Richman, Division of Engineering, Brown University, Providence, RI 02912
1	Mr. Ronald P. Tye, Energy Materials Testing Laboratory, Biddeford Industrial Park, Biddeford, ME 04005
1	Prof. Franklin E. Wawner, Department of Materials Science, School of Engineering and Applied Sciences, University of Virginia, Charlottesville, VA 22903
1	Dr. Carl Zweben, General Electric Company, Valley Forge Space Center/M4018, P.O.Box 8555, Philadelphia, PA 19101
	Director, U.S. Army Materials Technology Laboratory, Watertown, MA 02172-0001
2	ATTN: SLCMT-IML
2	Authors

U.S. Army Materials Technology Laboratory,
Watertown, Massachusetts 02172-0001
THE EFFECT OF NOTCH ROOT RADIUS ON THE
DETERMINATION OF TOUGHNESS IN ULTRAHIGH
STRENGTH STEEL FRICTION WELDS -
William S. Ricci and Eric B. Kulak

Technical Report MTL TR 88-21, June 1988, 5 pp
illus, tables, D/A Project IL2631020071

AD

UNCLASSIFIED
UNLIMITED DISTRIBUTION
Key Words

Welding
Inertia
Friction

The plain strain fracture toughness and Charpy impact energy of friction welds in ultrahigh strength AISI 4340 steel were determined. Fracture toughness values for the weld zone were found to exceed those of the base metal. This is believed to be due to the larger prior austenite grain size in the weld zone resultant from the weld thermal cycle. Charpy impact energy data for the weld zone, however, were approximately 50 percent lower than those of the base metal. This was due to the adverse reorientation of sulfide inclusions in the weld zone resulting from the forging stage of the welding cycle. Discrepancies between fracture toughness and Charpy impact test data can be attributed to notch root radius effects. The use of both sharp notch and rounded notch toughness tests are recommended for the determination of weld joint ductility in ultrahigh strength steels.

AD

U.S. Army Materials Technology Laboratory,
Watertown, Massachusetts 02172-0001
THE EFFECT OF NOTCH ROOT RADIUS ON THE
DETERMINATION OF TOUGHNESS IN ULTRAHIGH
STRENGTH STEEL FRICTION WELDS -
William S. Ricci and Eric B. Kulak

Technical Report MTL TR 88-21, June 1988, 5 pp
illus, tables, D/A Project IL2631020071

UNCLASSIFIED
UNLIMITED DISTRIBUTION
Key Words

Welding
Inertia
Friction

The plain strain fracture toughness and Charpy impact energy of friction welds in ultrahigh strength AISI 4340 steel were determined. Fracture toughness values for the weld zone were found to exceed those of the base metal. This is believed to be due to the larger prior austenite grain size in the weld zone resultant from the weld thermal cycle. Charpy impact energy data for the weld zone, however, were approximately 50 percent lower than those of the base metal. This was due to the adverse reorientation of sulfide inclusions in the weld zone resulting from the forging stage of the welding cycle. Discrepancies between fracture toughness and Charpy impact test data can be attributed to notch root radius effects. The use of both sharp notch and rounded notch toughness tests are recommended for the determination of weld joint ductility in ultrahigh strength steels.

U.S. Army Materials Technology Laboratory,
Watertown, Massachusetts 02172-0001
THE EFFECT OF NOTCH ROOT RADIUS ON THE
DETERMINATION OF TOUGHNESS IN ULTRAHIGH
STRENGTH STEEL FRICTION WELDS -
William S. Ricci and Eric B. Kulak

Technical Report MTL TR 88-21, June 1988, 5 pp
illus, tables, D/A Project IL2631020071

AD

UNCLASSIFIED
UNLIMITED DISTRIBUTION
Key Words

Welding
Inertia
Friction

The plain strain fracture toughness and Charpy impact energy of friction welds in ultrahigh strength AISI 4340 steel were determined. Fracture toughness values for the weld zone were found to exceed those of the base metal. This is believed to be due to the larger prior austenite grain size in the weld zone resultant from the weld thermal cycle. Charpy impact energy data for the weld zone, however, were approximately 50 percent lower than those of the base metal. This was due to the adverse reorientation of sulfide inclusions in the weld zone resulting from the forging stage of the welding cycle. Discrepancies between fracture toughness and Charpy impact test data can be attributed to notch root radius effects. The use of both sharp notch and rounded notch toughness tests are recommended for the determination of weld joint ductility in ultrahigh strength steels.

AD

U.S. Army Materials Technology Laboratory,
Watertown, Massachusetts 02172-0001
THE EFFECT OF NOTCH ROOT RADIUS ON THE
DETERMINATION OF TOUGHNESS IN ULTRAHIGH
STRENGTH STEEL FRICTION WELDS -
William S. Ricci and Eric B. Kulak

Technical Report MTL TR 88-21, June 1988, 5 pp
illus, tables, D/A Project IL2631020071

UNCLASSIFIED
UNLIMITED DISTRIBUTION
Key Words

Welding
Inertia
Friction

The plain strain fracture toughness and Charpy impact energy of friction welds in ultrahigh strength AISI 4340 steel were determined. Fracture toughness values for the weld zone were found to exceed those of the base metal. This is believed to be due to the larger prior austenite grain size in the weld zone resultant from the weld thermal cycle. Charpy impact energy data for the weld zone, however, were approximately 50 percent lower than those of the base metal. This was due to the adverse reorientation of sulfide inclusions in the weld zone resulting from the forging stage of the welding cycle. Discrepancies between fracture toughness and Charpy impact test data can be attributed to notch root radius effects. The use of both sharp notch and rounded notch toughness tests are recommended for the determination of weld joint ductility in ultrahigh strength steels.

END

DATE

FILMED

DTIC

9-88